

Tender specifications LIVING STONES collection

Supply of Blustyle by Cotto d'Este porcelain stoneware tiles for walls and floors.

Product characteristics

Blustyle by Cotto d'Este full body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Compliance with EN 14411-G / ISO 13006-G

The Living Stones collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Blustyle by Cotto d'Este in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit). The product contains no VOC (volatile organic compounds) and has obtained the GREENGUARD GOLD certification. The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Living Stones collection based on its Life Cycle Assessment (LCA).

Commercial description of the product

Company	BLUESTYLE by COTTO D'ESTE (Panariagroup Industrie Ceramiche S.p.A.)	
Collection	LIVING STONES	
Colours	LIGHT CREAM, STONE BEACH, BASALT GREY	
Sizes	60X60cm Thick. 10mm	60X60cm Grip Thick. 20mm
	45X90cm Thick. 11mm	
	90X90cm Thick. 11mm	
Surfaces	NATURAL (NAT), HONED (LAP), GRIP	
Edges	RECTIFIED (RECT)	
Thickness	9,5mm - 20mm	



EMAS



ISO 14001



40%



LEED



LEED



GREENGUARD
GOLD



ISO 9001



MARCHIO CE



MADE IN ITALY



EPD

Tender specifications LIVING STONES collection

Technical features

Product type: full body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G, EN 14411-G	Average values LIVING STONES
Water absorption		ISO 10545-3	≤ 0,5 %	0,05 %
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Thick. 9,5mm: 2.500 N Thick. 20mm: 13.600 N
Modulus of rupture		ISO 10545-4	≥ 35 N/mm ²	50 N/mm ²
Deep abrasion resistance		ISO 10545-6	≤ 175mm ³	145mm ³
Linear thermal expansion		ISO 10545-8	No provision	$\alpha \leq 7 \cdot 10^{-6} \text{ } ^\circ\text{C}^{-1}$
Stain resistance		ISO 10545-14	Class 3 Min.	5 RESISTANT
Chemical resistance (*)		ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance		ISO 10545-12	No alteration	RESISTANT
Dimensions	Lenght and width	ISO 10545-2	Bordi Rett. ± 0,3 %, max ± 1 mm Bordi Non Rett. ± 0,6 %, max ± 2 mm	COMPLIANT
	Straightness of sides	ISO 10545-2	Bordi Rett. ± 0,3 %, max ± 0,8 mm Bordi Non Rett. ± 0,5 %, max ± 1,5 mm	COMPLIANT
	Rectangularity	ISO 10545-2	Bordi Rett. ± 0,3 %, max ± 1,5 mm Bordi Non Rett. ± 0,5 %, max ± 2 mm	COMPLIANT
	Warpage	ISO 10545-2	Bordi Rett. ± 0,4 %, max ± 1,8 mm Bordi Non Rett. ± 0,5 %, max ± 2 mm	COMPLIANT
	Thickness	ISO 10545-2	± 5 %, max ± 0,5mm	COMPLIANT
Slip resistance	DIN 51130	-	-	R10 (NAT) R11 (GRIP)
	DIN 51097	-	-	A+B+C (GRIP)
	BCR-TORTUS	-	-	$\mu > 0,40$ (NAT, GRIP)
	ANSI A326.3	-	-	DCOF≥0.42 (Not Basalt Grey Lap.)
	BS 7976-2	-	-	PTV 36+ Slider 55 (GRIP)
	UNE ENV 12633	-	-	Clase 1 (NAT E LAPP.) Clase 3 (GRIP)
Shade variation		ANSI A 137.1	As indicated by manufacturer	V2
Flame spread		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A1 (wall)
		EN 9239-1		Class A1 _{fl} (floor)
Thermal conductivity		EN 12524	-	$\lambda = 1,3 \text{ W/m } ^\circ\text{K}$
Recommended minimum joint (**)		Indoor	-	2mm (RECT)

(*) Excluding hydrofluoric acid and its derivatives.

(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.



EMAS



ISO 14001



40%



LEED



LEED



GREENGUARD
GOLD



ISO 9001



EN 14411

La DGP sono disponibili sul sito internet www.panarigroup.it
DGP are available on the website www.panarigroup.it

MARCHIO CE



MADE IN ITALY



EPD